


Early consideration and allowance are respectfully requested.

Respectfully submitted,

Date: July 27, 2001


John B. Alexander, Ph.D. (Reg. No. P-48,399)
DIKE, BONSTEIN, ROBERTS & CUSHMAN
Intellectual Property Practice Group
EDWARDS & ANGELL, LLP
P.O. Box 9169
Boston, MA 02209


(617) 439-4444

09/15/00 09:29:01

APPENDIX

IN THE SPECIFICATION

On page 21, rewrite formula (9) as



On page 95, rewrite the second paragraph as

A hydroxyethylation reaction of acrylic acid was carried out by using the polymer gel that had been formed by allowing the polymer (6) obtained in Embodiment 6 to swell in the reaction solution as a catalyst through the same reactions and operations as those of Embodiment 28 except that the polymer (6) [grainy resin (5)] obtained in Embodiment 6 was used instead of the grainy resin (5) obtained in Embodiment 5.

IN THE CLAIMS

14. (new) An method for addition of a heterocyclic compound or an aldehyde to an active-hydrogen-containing compound, comprising the steps of

activating an active-hydrogen-containing compound with a polymer gel having a cyclic amine structure or a cyclic quaternary ammonium salt structure in the presence of a heterocyclic compound or an aldehyde under conditions conducive to the addition of the heterocyclic compound or the aldehyde to the active-hydrogen-containing compound.

15. (new) The addition method of claim 14, wherein:
the active-hydrogen-containing compound is a compound selected from the group consisting of phenols, amides, alcohols, and carboxylic acids; and
the heterocyclic compound is an oxirane compound.

16. (new) The addition method of claim 14, wherein the polymer gel has a three-dimensional network structure holding solvent inside thereof and also has active sites for activating the active-hydrogen-containing compound inside the three-dimensional network structure and/or on the surface thereof.

17. (new) The addition method of claim 14, wherein the cyclic amine structure or the cyclic quaternary ammonium salt structure in the polymer gel is derived from at least one selected from the group consisting of *N,N,N*-triallylamines, *N,N*-diallylamines, and dialyldimethylammonium chlorides.

18. (new) The addition method of claim 14, wherein the polymer gel has a ratio of swell of not less than 2.

19. (new) The addition method of claim 14, wherein the polymer gel has a thermal decomposition temperature, that is, a heat-absorption peak temperature on a TG-DTA curve obtained when the polymer gel is heated at a rate of 5°C/min in a nitrogen gas flow, of not less than 300 °C.

20. (new) A method for manufacturing a hydroxyalkyl(meth)acrylate comprising the step of

00945700-02204

activating (meth)acrylate with a polymer gel having a cyclic amine structure or a cyclic quaternary ammonium salt structure in the presence of an oxirane under conditions conducive to the addition of the oxirane to the (meth)acrylate to form a hydroxyalky(meth)acrylate.

102220-00251600